




aitex®
research & innovation center



SIMPLIFIED TEST REPORT No. 2024CN0340

Issued by Aitex on 11/06/2024

AITEX declares that the article/s:

Reference:

FABRIC DP-ARC-PF1-250W

According to the customer:

Composition and percentage: Arc protection

Style: Twill

Color: Dark Navy

Weight: 250 g/m²

Manufacturer: Wuxi Deep-Protection Textile
Science & Technology Co.,Ltd

Given by the company:

WUXI DEEP-PROTECTION TEXTILE SCIENCE
& TECHNOLOGY CO.,LTD
No.36,Yanjin RD,Huishan
District,Wuxi,Jiangsu,Chin
CN-214174 WUXI
China

Has/have been tested according to:

ELECTRIC ARC EXPOSURE TEST: DETERMINATION OF THE ARC RATING (ELIM, ATPV OR E_{BT50}) OF FLAME RESISTANT MATERIALS FOR CLOTHING

Standard:

EN IEC 61482-1-1: 2019 Material test (Procedure A)

Getting the following results:

ARC RATING (ATPV)	13 cal/cm ²
ELIM	11 cal/cm ²

Pre-treatment:

5 washing cycles at 30°C, according to standard EN ISO 6330:2021, method 3N and tumble drying (A).

The test results above indicated are shown in the testing
report/s:

2024CN0339

Signed by:



Firmado digitalmente
por [ISABEL LLOPIS]
LUMBRERAS
Fecha: 2024.06.11
13:39:37 +02'00'

Lucía Martínez
Head of PPE and Ballistic department

The test was carried out at Polígono Industrial Fuente del Jarro. C/ Ciudad de Gibraltar, 5; 46988 - Paterna (Valencia); which property is shared at 50% between research institutes AITEX and ITE

(1)The Essential test data and liability clauses are included at indicated test report number and are at the applicant's disposal.

1/1



aitex®
research & innovation center



ITE
INSTITUTO TECNOLÓGICO DE
LA ENERGÍA